

Superseded 7/1/2016**15A-3-108 Amendments to Chapters 17 through 19 of IBC.**

- (1) A new IBC, Section 1807.1.6.4, is added as follows: "1807.1.6.4 Empirical concrete foundation design. Group R, Division 3 Occupancies three stories or less in height, and Group U Occupancies, which are constructed in accordance with Section 2308, or with other methods employing repetitive wood-frame construction or repetitive cold-formed steel structural member construction, shall be permitted to have concrete foundations constructed in accordance with Table 1807.1.6.4."
- (2) A new IBC, Table 1807.1.6.4 is added as follows:

"TABLE 1807.1.6.4							
EMPIRICAL FOUNDATION WALLS (1,7,8)							
Max. Height	Top Edge Support	Min. Thickness	Vertical Steel (2)	Horizontal Steel (3)	Steel at Openings (4)	Max. Lintel Length	Min. Lintel Length
2'(610 mm)	None	6"	(5)	2- #4 Bars	2- #4 Bars above 1- #4 Bar each side 1- #4 Bar below	2'(610 mm)	2" for each foot of opening width; min. 6"
3'(914 mm)	None	6"	#4@32"	3- #4 Bars	2- #4 Bars above 1- #4 Bar each side 1- #4 Bar below	2'(610 mm)	2" for each foot of opening width; min. 6"
4'(1,219 mm)	None	6"	#4@32"	4- #4 Bars	2- #4 Bars above 1- #4 Bar each side 1- #4 Bar below	3'(914 mm)	2" for each foot of opening width; min. 6"
6'(1,829 mm)	Floor or roof Diaphragm (6)	8"	#4@24"	5- #4 Bars	2- #4 Bars above 1- #4 Bar each side 1- #4 Bar below	6'(1,829 mm)	2" for each foot of opening width; min. 6"
8'(2,438 mm)	Floor or roof Diaphragm (6)	8"	#4@24"	6- #4 Bars	2- #4 Bars above 1- #4 Bar each side 1- #4 Bar below	6'(1,829 mm)	2" for each foot of opening width; min. 6"

9'(2,743 mm)	Floor or roof Diaphragm (6)	8"	#4@16"	7- #4 Bars	2- #4 Bars above 1- #4 Bar each side 1- #4 Bar below	6'(1,829 mm)	2" for each foot of opening width; min. 6"
Over 9'(2,743 mm), Engineering required for each column							
Footnotes:							
(1) Based on 3,000 psi (20.6 Mpa) concrete and 60,000 psi (414 Mpa) reinforcing steel.							
(2) To be placed in the center of the wall, and extended from the footing to within three inches (76 mm) of the top of the wall; dowels of #4 bars to match vertical steel placement shall be provided in the footing, extending 24 inches (610 mm) into the foundation wall.							
(3) One bar shall be located in the top four inches (102 mm), one bar in the bottom four inches (102 mm) and the other bars equally spaced between. Such bar placement satisfies the requirements of Section 1805.9. Corner reinforcing shall be provided so as to lap 24 inches (610 mm).							
(4) Bars shall be placed within two inches (51 mm) of the openings and extend 24 inches (610 mm) beyond the edge of the opening; vertical bars may terminate three inches (76 mm) from the top of the concrete.							
(5) Dowels of #4 bar at 32 inches on center shall be provided in the footing, extending 18 inches (457 mm) into the foundation wall.							
(6) Diaphragm shall conform to the requirements of Section 2308.							
(7) Footing shall be a minimum of nine inches thick by 20 inches wide.							
(8) Soil backfill shall be soil classification types GW, GP, SW, or SP, per Table 1610.1. Soil shall not be submerged or saturated in groundwater."							

- (3) In IBC, Section 1904.2, a new exception 1 is added as follows and the current exception is modified to be number 2.

Exceptions:

"1. In ACI Table 4.3.1, for Exposure Class F1, change Maximum w/cm from 0.45 to 0.5 and Minimum f'c from 4,500 psi to 3,000 psi."

- (4) A new IBC, Section 1905.1.11, is added as follows: "1905.1.11 ACI 318, Table 4.2.1." Modify ACI 318, Table 4.2.1 to read as follows: In the portion of the table designated as "Conditions", the Exposure categories and classes are deleted and replaced with the following:
- "F0: Concrete elements not exposed to freezing and thawing cycles to include footing and foundation elements that are completely buried in soil.
- F1: Concrete elements exposed to freezing and thawing cycles and are not likely to be saturated or exposed to deicing chemicals.
- F2: Concrete elements exposed to freezing and thawing cycles and are likely to be saturated, but not exposed to deicing chemicals.
- F3: Concrete elements exposed to freezing and thawing cycles and are likely to be saturated and exposed to deicing chemicals."